

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau




INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<p>(51) International Patent Classification ⁶ : A61B 17/80</p>	<p>A1</p>	<p>(11) International Publication Number: WO 98/09578 (43) International Publication Date: 12 March 1998 (12.03.98)</p>
<p>(21) International Application Number: PCT/IT97/00217 (22) International Filing Date: 1 September 1997 (01.09.97) (30) Priority Data: GE96A000076 4 September 1996 (04.09.96) IT (71)(72) Applicants and Inventors: MAGRINI, Anna [IT/IT]; Via Brigata Salerno, 2/1, I-16147 Genova (IT). CARTA, Maurizio [IT/IT]; Via Giovanni Bertora, 1, I-16122 Genova (IT).</p>		<p>(81) Designated States: AL, AU, BA, BB, BG, BR, CA, CN, CU, CZ, EE, GE, HU, IL, IS, JP, KP, KR, LC, LK, LR, LT, LV, MG, MK, MN, MX, NO, NZ, PL, RO, SG, SI, SK, SL, TR, TT, UA, US, UZ, VN, YU, ARIPO patent (GH, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).</p> <p>Published <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i></p>

(54) Title: PRODUCTION PROCESS OF VARYING THICKNESS OSTEOSYNTHESIS PLATES

(57) Abstract

The invention concerns a process for the production of osteosynthesis plates with a varying thickness thin to whatever degree. The plates are manufactured by a metal cutting process carried out on a composite structure made by a layer of the material which will form the osteosynthesis plate, bound through a layer of adhesive to a supporting layer with high thermal conductivity and mechanical strength. When the cutting process terminates, the osteosynthesis plate is separated from the supporting layer by heating the composite structure until the adhesive melts or by using a thinner suitable for the adopted adhesive.



FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NI	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

DescriptionProduction Process of Varying Thickness
Osteosynthesis Plates

5

Technical Field

The invention relates to a process for the production of plates for osteosynthesis with a varying thickness thin to whatever degree.

10

Background Art

Plates which are presently used to achieve osteosynthesis have a constant thickness due to the adopted production process. Said process
15 consists in cutting, usually by laser, the plate from a sheet of biocompatible metal characterised by a constant thickness, following the plate contour, and in making the countersink holes for the screws heads by plastic deformation of the
20 metal around the holes.

Osteosynthesis plates with constant thickness should have a thickness dimensioned in order to bear the tension in the most stressed section near the fracture or osteotomy line (proximal area).
25 This thickness is however greater than the thickness required by the stress present in the sections farther from proximal area (distal areas). In these areas the adjustment of the plate to the bone surface done by bending can therefore
30 be more difficult than needed. Another consequence of the constant thickness is that in the distal areas the elastic component of the deformation adopted to fit the plate to the bone geometry is greater than that resulting from a smaller
35 thickness; unwanted stresses and displacements of the bone segments connected by the plate may be experienced.

In general the complex shape, the small size, the limited thickness in the proximal and distal areas of the plate make difficult the manufacturing of plates by metal cutting processes which would be necessary to obtain varying thickness, unless a system for fixing adequately the machined plate is available.

Fixing systems of magnetic type do not work with biocompatible materials such as titanium and stainless steel generally used for osteosynthesis plates. Other clamping systems of mechanical type in which the fastening is carried out by pressure on the workpiece do not permit to machine the plate without interruptions for changing the clamping zone and completing the operation in the plate areas previously hidden by the clamping device. The mechanical fastening doesn't prevent deformation and fracture in the plate areas with a small thickness since cutting loads can create stress conditions which cannot be allowed by the strength of the plate material. Moreover mechanical clamping may leave marks on the surface of the ductile materials used for the production of plates.

Fixing the workpiece by embedding in resin has the disadvantage of a poor dissipation of the heat produced during the workpiece cutting due to the inadequate thermal conductivity of the resin. Consequently the resin temperature increases determining the softening of the resin and the reduction of the resin binding capability necessary to keep the workpiece during the cutting process.

These drawbacks impede the industrial manufacturing by means of metal cutting processes, of osteosynthesis plates with a varying thickness and therefore prevent the achievement of the

biomechanical advantages coming from the variation of the plate thickness.

Disclosure of Invention

5 According to the invention these problems are solved by making a composite structure consisting of a plate of the material which will form the osteosynthesis plate, of (structural) adhesive and of a bearing plate with an adequate strength and
10 high thermal conductivity able to dissipate the heat produced during the cutting, so that from this composite structure, once the desired shape and thickness profile of the osteosynthesis plate have been obtained by a metal cutting process, the
15 osteosynthesis plate could be separated from the bearing plate by melting the adhesive through the heating of the composite structure to a temperature greater than 80°C or through a thinner.

20 The invented process is based on the fact that the composite structure manufactured in the said way, gives to the layer of the material which will become the osteosynthesis plate, a structural strength able to resist to the stress produced by
25 the metal cutting. The size of the composite structure can be set in such a way to permit the mechanical clamping of the composite structure to the machine tool by using commercially available fixing devices. The heat generated by the metal
30 cutting is dissipated by the bearing layer thank to its high thermal conductivity, avoiding in this way the heating of the adhesive layer above temperature at which the softening of the adhesive begins. The final separation of the plate from the
35 bearing layer is carried out by exploiting the softening of the adhesive layer which usually for structural adhesives appears at temperature over

80°C. Otherwise it is possible to melt the adhesive layer by adopting a thinner suitable for the employed adhesive.

The main advantage of the invented process consists in making possible the production of osteosynthesis plate with a varying thickness, thin to whatever degree, by adopting a metal cutting machining overcoming the above mentioned technological problems due to the fixing of the plate by clamping or by embedding in resin. Another important intent of the invention consists in making possible the manufacture of osteosynthesis plates with a varying thickness characterised by a better fitting to the bone surface. Another important aim of the invention consists in making possible the manufacture of osteosynthesis plates with varying thickness giving limited stress and relative displacements of the connected bone segments. The invented process permits moreover the production of osteosynthesis plates with a varying thickness in an easy and economical way without the need of complex technologies and skilled labour.

25 Description of Drawings

Figure 1 and figure 2 show respectively the plan view and the lateral view of an example of an osteosynthesis plate which can be manufactured by the invented process. Figure 3 and figure 4 display respectively the plan view and the cross sectional view of the composite structure which is machined in order to manufacture the osteosynthesis plate.

35 Best Mode of Carrying Out the Invention

The best mode of carrying out the invented process is described considering the manufacturing

of the osteosynthesis plate with reference to the accompanying drawings. The plate material is commercially pure titanium. The shape of the plate, indicated in figure 1, is an example of an osteosynthesis plate with a double Y configuration characterised by different thickness in the proximal area 1 and in the distal areas 2. Thickness in the proximal area is 1.00 mm, thickness in the distal areas is 0.50 mm. The production process requires to manufacture the composite structure (figures 3, 4) consisting of a commercially pure titanium sheet (3) with a thickness of 1.05 mm, bound by a cyanoacrylate layer (5) to an aluminium sheet (4). The aluminium sheet is larger than the titanium plate, and its thickness is 4 mm. The composite structure is clamped to the worktable of a milling machine which performs the drilling operations, the surfaces generation according to the required thickness, the contouring of the plate cutting completely the titanium layer. Once the machining has been carried out, the osteosynthesis titanium plate is separated from the bearing aluminium layer by heating the composite structure at a temperature greater than 80°C in order to melt the adhesive layer.

Alternative ways of carrying out the invented process include other biocompatible plate materials, other bearing plate materials with high thermal conductivity, other types of structural adhesives, other thickness of the composite structure layers, other compatible heating temperatures or alternatively an adhesive thinner.

Claims

1. A process for manufacturing osteosynthesis plates with a varying thickness characterised by
5 making, by using an adhesive, a composite structure consisting of a plate of the material which will form the osteosynthesis plate, of the adhesive and of a bearing plate with an adequate strength and high thermal conductivity able to
10 dissipate the heat produced during the cutting, so that from this composite structure, once the desired shape and thickness profile of the osteosynthesis plate have been obtained by a metal cutting process, the osteosynthesis plate could be
15 separated from the bearing plate by melting the adhesive through the heating of the composite structure to a temperature greater than 80°C or through a thinner.





FIG 3





FIG 4



INTERNATIONAL SEARCH REPORT

Int ional Application No
PCT/IT 97/00217

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 A61B17/80

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 6 A61B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 4 683 878 A (D.R.CARTER) 4 August 1987 see figure 1 ---	1
A	EP 0 266 146 A (JOHNSON AND JOHNSON) 4 May 1988 see abstract ---	1
A	US 3 894 633 A (J.J.EGAN) 15 July 1975 see column 1, line 15 - line 19 see column 1, line 32 - line 35 -----	1

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

19 December 1997

Date of mailing of the international search report

02/01/1998

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl.
Fax: (+31-70) 340-3016

Authorized officer

Nice, P

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/IT 97/00217

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 4683878 A	04-08-87	NONE	
EP 0266146 A	04-05-88	AU 602732 B	25-10-90
		AU 8014987 A	28-04-88
		CA 1306156 A	11-08-92
		DE 3783324 A	11-02-93
		JP 2081344 C	09-08-96
		JP 7102213 B	08-11-95
		JP 63186642 A	02-08-88
		KR 9600622 B	10-01-96
		US 4905680 A	06-03-90
US 3894633 A	15-07-75	NONE	